

CT 83

STRONG FIX


Adhesive mortar for EPS



For fixing Expanded Polystyrene boards for thermal insulation of buildings by means of ETICS

CHARACTERISTICS

- ▶ high adhesion to mineral substrates and EPS-boards
- ▶ very good working parameters
- ▶ weather conditions resistant
- ▶ possibility of machine application



SCOPE OF USE

Ceresit CT 83 mortar is designed to apply EPS and XPS-boards within Ceresit ETICS (External Thermal Insulation Composite Systems) with a light-wet method Ceresit Ceretherm. CT 83 mortar is used for applying to the newly erected objects as well as the buildings to be thermo renovated. The applied boards require additional fixing by means of mechanical anchors, i.e. proper expansion pins made of plastic.

Ceresit CT 85, CT 87 or CT 100 mortar should be used to apply fibre glass armoured layer on the EPS-boards.

In case of the walls insulation with façade mineral wool boards, Ceresit CT 190, CT 180 or CT 87 mortar should be used.

SUBSTRATE PREPARATION

CT 83 shows very good adhesion to sound and carrying substrates, such as wall, plaster and cement substrates free from grease, bitumen, dust and other substances decreasing adhesion.

The adhesion to the existing plasters and paint coatings should be checked before starting the application. "Hollow" plasters should be removed. Any losses and uneven surfaces of the substrate below 20 mm should be filled with the filler CT 29 or covered with cement plaster. Any surface contaminant and other adhesion impairing substances, steam-tight paint coatings and the coats with low adhesion to the substrate should be completely removed, e.g. by means of washing devices operating under pressure. In case of mycological contamination with fungi, moss and algae, the surface of the façade should be cleaned water under pressure with addition of the agent for removing impurities CT 98, if necessary clean the surface with steel brushes and, then saturated with a fungicide solution of Ceresit CT 99 in compliance



CERESIT C_CT83_TDS_1_0116

with technical instruction. The old, not plastered walls, strong plasters and paint coats should be dusted, then washed with water jet and left until they go completely dry. Substrates with high water absorption, e.g. walls made of aerated concrete blocks should be primed with Ceresit CT 17 and left for drying for at least 2 hours.

APPLICATION

CT 83 should be poured into the measured amount of cool clean water and stirred with the drill by means of a mixer until the homogenous mass is obtained without lumps, wait 5 minutes and mix again.

The ready mortar should be applied with a trowel along the board edges forming a strip of 3÷4 cm wide and a few spots with the diameter of approx. 8 cm. Then immediately, the board should be pressed to the wall with a few slight blows of a long float. The properly applied mortar when pressed should cover minimum 40 % of its surface. In case of even, smooth substrates the mortar should be applied by means of a toothed long float (teeth 10–12 mm). The boards should be fixed tightly one at the other in one surface with the preservation of "brick like manner" of vertical connection.

When CT 83 is set (after approx. 3 days), any unevenness of the boards should be ground with abrasive paper, then the boards should be additionally reinforced with mechanical anchors. The number of anchors should be min. 4 per m². The stripes of 2 m wide located along the building edge are exposed to the biggest wind powers and the number of anchors should be increased in these places up to min. 8 per m².

Possibility of mechanical application. Recommended type of machine e.g. Wagner PC 15 or SPG Baumaschinen PG 20 with the gun for mortar application.

Fresh stains should be cleaned with water while hardened elements should be mechanically removed only.

PLEASE NOTE

CT 83 powder mortar shows acrid properties, and cement and lime content causes alkali reaction when mixed with water. Therefore skin and eyes should be protected. In case of contact with eyes, they should be rinsed with water and the general practitioner should be consulted. The performance characteristics are given in the text of corresponding to the product Declaration of Performance. The previously issued technical data sheets become invalid with the issue of this technical data sheet.

The content of chromium VI – below 2 ppm till the expiry date.

PACKAGING

Bags of 25 kg.

Apart from the information given here it is also important to observe the relevant guidelines and regulations of various organisations and trade associations as well as the respective standards of the German Standards Institute (DIN). The aforementioned characteristics are based on practical experience and applied testing. Warranted properties and possible uses which go beyond those warranted in this information sheet require our written confirmation. All data given was obtained at an ambient and material temperature of +23 °C and 50 % relative air humidity unless specified otherwise. Please note that under other climatic conditions hardening can be accelerated or delayed.

The information contained herein, particularly recommendations for the handling and use of our products, is based on our professional experience. As materials and conditions may vary with each intended application, and thus are beyond our sphere of influence, we strongly recommend that in each case sufficient tests are conducted to check the suitability of our products for their intended use. Legal liability cannot be accepted on the basis of the contents of this data sheet or any verbal advice given, unless there is a case of wilful misconduct or gross negligence on our part. This technical data sheet supersedes all previous editions relevant to this product.



Henkel CEE
Erdbergstrasse 29
1030 Vienna
www.ceresit.com

TECHNICAL DATA

Base:	cement and lime mixture with mineral fillers and modifiers
Bulk density:	approx. 1.3 kg/dm ³
Mixing ratio:	4.75 ÷ 5.25 l of water per 25 kg
Temperature of application:	from +5 °C to +25 °C
Pot life:	up to 90 minutes
Compression resistance:	≥ 20 N/mm ² (CS IV) acc EN 1015-11:2001+A1:2007
Flexural resistance:	≥ 5,5 N/mm ² acc EN 1015-11:2001+A1:2007

Adhesion acc. ETAG 004:	
to concrete	≥ 0.25 MPa
to EPS boards	≥ 0.08 MPa

Reaction to fire class acc. EN 13501-1:

B – s1, d0 in:

Ceresit Ceretherm Popular, Ceresit Ceretherm Classic
Ceresit Ceretherm Premium

B – s2, d0 in:

Ceresit Ceretherm Impactum

Assessment of natural radiation: meets the requirements of ITB Instruction No. 234/2003, p.6.2.1, according to Regulation of the Council of Ministers on 2 January 2007. & 3, p.1

Assumed consumption: approx. 5.0 kg/m²

Shelf life/ Storage: Up to 12 months since the production date when stored on pallets in dry cool conditions and in original undamaged packages.

This product possesses documents of reference:

- BBA Certificate No. 14/5142
- Irish Agreement Board Certificate No. 09/0340
- European Technical Approval (ETA) in systems:

Ceresit Ceretherm System	Classic	Premium	Visage	Visage TR	Impactum
ETA	09/0014	08/0308	11/0395	15/0198	13/0086
Certificate	1488-CPD-0104/W	1488-CPR-0363/Z	1488-CPR-0370/Z	1488-CPR-0370/Z	1488-CPR-0407/Z
DoP	00420/1-07-2013	00428/06-08-2014	00431/24-06-2015	00431TR/24-06-2015	00436/17-09-2015

- Technical Approvals in Systems:

Ceresit Ceretherm System	Classic	Ceramic	Reno	Visage
TA	15-4397 /2013	15-7027/2011 + Annexes	15-8077 /2009 + Annexes	15-8399/2011
Certificate	ITB-0109/Z	ITB-0137/Z	ITB-0355/Z	ITB-0416/Z
DoC	00440/01-07-2013	00439/15-04-2014	00444/12-08-2015	00445/01-07-2013

Quality for Professionals